# S2130

## (UL ANSI: CEM-3.0)

#### **FEATURES**

- Punching process capability
- Excellent electrical properties
- PTH reliability equivalent to FR-4.0
- Non-UV Blocking

## APPLICATIONS

Game machine, Remote control unit Household appliances, Automotive electronics, Apparatus, and instrument For applications with CAF requirements, recommend customer to carry a systematic assessment of its reliability.

Test Items	Test Method	Test Condition	Unit	Typical Value
Tg	IPC-TM-650 2.4.25D DSC °C 1		130	
Thermal Stress	IPC-TM-650 2.4.13.1 288°C , solder dip		S	>30
	IPC-TM-650 2.4.24	Before Tg	ppm/°C	60
CTE (Z-axis)	IPC-TM-650 2.4.24	After Tg	ppm/°C	340
	IPC-TM-650 2.4.24	50-260°C	%	5.2
Permittivity (1MHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	4.6
Loss Tangent (1MHz)	IPC-TM-650 2.5.5.9	C-24/23/50	-	0.016
Volume Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	MΩ-cm	2.9×10 <sup>8</sup>
Surface Resistivity	IPC-TM-650 2.5.17.1	C-96/35/90	MΩ	2.8×10 <sup>7</sup>
Arc Resistance	IPC-TM-650 2.5.1	D-48/50+D-0.5/23	S	115
Dielectric Breakdown	IPC-TM-650 2.5.6	D-48/50+D-0.5/23	kV	>45
Peel Strength (1oz)	eel Strength (1oz) IPC-TM-650 2.4.8		N/mm [lb/in]	1.9 [10.86]
Flexural Strength (LW/CW)	Flexural Strength (LW/CW) IPC-TM-650 2.4.4		Мра	400/320
Water Absorption	IPC-TM-650 2.6.2.1	D-24/23	%	0.11
Flammability	UL94	C-48/23/50	Rating	V-0
СТІ	IEC60112	A	Rating	PLC 3

## **GENERAL PROPERTIES**

Remarks : 1. Specification sheet: IPC-4101/12, is for your reference only.

2. All the typical value is based on the 1.6mm specimen.

3. All the typical value listed above is for your reference only, please turn to Shengyi Technology Co., Ltd for detailed information, and all rights from this data sheet are reserved by Shengyi Technology Co., Ltd.

## **PURCHASING INFORMATION**

Thickness	Copper foil	Standard size
0.63mm to 3.2mm	18um to 105 um	915mm×1,220mm(36"×48") 1,020mm×1,220mm(40"×48")
		1,070mm×1,220mm(42″×48″)

Remarks: Other sheet size and thickness could be available upon request.